



TEMA

Technologies
Engineering
Materials
Architecture

Journal Director: R. Gulli

e-ISSN 2421-4574

Vol. 7, No. 1 (2021)

Issue edited by Editor in Chief: R. Gulli

Cover illustration: Azulejos, Casa de Pilatos, Seville. © Renato Morganti, 2017

Editorial Assistants: C. Mazzoli, D. Prati



e-ISSN 2421-4574

Vol. 7, No. 1 (2021)

Year 2021 (Issues per year: 2)

Journal Director

Riccardo Gulli

Scientific Committee

Construction History and Preservation

Santiago Huerta, Antonio Becchi, Camilla Mileto, Amedeo Bellini, Stefano Della Torre, Alberto Grimoldi, Claudio Varagnoli, Tullia Iori, Antonello Sanna, Renato Morganti, Giovanni Fatta, Marco Dezzi Bardeschi, Corrado Fianchino

Construction and Building Performance

Matheos Santamuris, Francisco Javier Neila González, M. Hyle, John Richard Littlewood, Gianfranco Carrara, Riccardo Nelva, Enrico Dassori, Marina Fumo

Building and Design Technology

Maurizio Brocato, José Luis Gonzalez, Emilio Pizzi, Francesco Polverino, Raffaella Lione, Angelo Salemi, Giorgio Cacciaguerra, Enrico Sicignano, Antonella Guida

Editor in Chief

Riccardo Gulli

Assistant Editors

Marco D'Orazio, Annarita Ferrante, Enrico Quagliarini

Editorial Assistants

Cecilia Mazzoli, Davide Prati

Scientific Society Partner:

Ar.Tec. Onlus

c/o DICEA, Università Politecnica delle Marche,

Polo Montedago, Via Brecce Bianche 12

60131 Ancona - Italy

Phone: +39 071 2204587

Email: info@artecweb.org- tema@artecweb.org

Media Partner:

Edicom Edizioni

Via I Maggio 117

34074 Monfalcone (GO) - Italy

Phone: +39 0481 484488

TEMA: Technologies Engineering Materials Architecture**Vol. 7, No. 1 (2021)**

e-ISSN 2421-4574

Editorial**Discipline and research: borders and frontiers***Renato Morganti*

DOI: 10.30682/tema0701a

5

CONSTRUCTION HISTORY AND PRESERVATION**Representation and knowledge of historic construction:****HBIM for structural use in the case of Villa Palma-Guazzaroni in Terni***Edoardo Currà, Alessandro D'Amico, Marco Angelosanti*

DOI: 10.30682/tema0701b

8

Displacement and deformation assessment of timber roof trusses through parametric modelling.**The case of San Salvatore's church in Bologna***Davide Prati, Luca Guardigli, Giovanni Mochi*

DOI: 10.30682/tema0701c

21

Planned maintenance for architectural heritage.**Experiences in progress from 3D survey to intervention programmes through HBIM***Marco Zerbinatti, Francesca Matrone, Andrea Lingua*

DOI: 10.30682/tema0701d

32

An interdisciplinary approach for the investigation and dating of Roman thermal buildings:**the Indirizzo Baths at Catania, Sicily***Anna Maria Gueli, Mariangela Liuzzo, Giuseppe Margani, Stefania Pasquale, Giuseppe Politi, Giuseppe Stella*

DOI: 10.30682/tema0701e

43

CONSTRUCTION AND BUILDING PERFORMANCE**Evolution of a patent work applied:****formulation of sustainable mortars with a new natural hydraulic binder on site***Santi Maria Cascone, Giuseppe Antonio Longhitano, Matteo Vitale, Giuseppe Russo, Nicoletta Tomasello*

DOI: 10.30682/tema0701f

67

The effects of mortar on the dynamic thermal performances of stone masonries

77

Giuseppe Desogus

DOI: 10.30682/tema0701g

Forest products in construction: a comparative life cycle assessment of an Italian case study

86

Giuliana Iannaccone, Francesco Pittau, Giovanni Dotelli

DOI: 10.30682/tema0701h

BUILDING AND DESIGN TECHNOLOGIES**Hospital architecture and the challenge of humanisation. Research and design**

96

Marco Morandotti, Daniela Besana

DOI: 10.30682/tema0701i

Innovative construction materials: graphene-based smart composites

107

Salvatore Polverino, Renata Morbiducci, Antonio E. Del Rio Castillo, Francesco Bonaccorso

DOI: 10.30682/tema07011

EVOLUTION OF A PATENT WORK APPLIED: FORMULATION OF SUSTAINABLE MORTARS WITH A NEW NATURAL HYDRAULIC BINDER ON SITE

Santi Maria Cascone, Giuseppe Antonio Longhitano,
Matteo Vitale, Giuseppe Russo, Nicoletta Tomasello

DOI: 10.30682/tema0701f



e-ISSN 2421-4574
Vol. 7, No. 1 - (2021)

This contribution has been peer-reviewed.
© Authors 2020. CC BY 4.0 License.

Highlights

Formulation of a patented mortar with no soluble elements.
Compliance with the historical morphology of the buildings.
Observance of the principles of circular economy by reusing aggregates of the building site.
Achievement of a low environmental impact thanks to the possibility of formulating the mortar on site.
Obtaining a possible alternative to Portland cement with excellent durability.

Abstract

The present research study concerns the formulation of natural mortars with hydraulic behaviour, used for the restoration of the walls of historical buildings. The research aim – based on a patented procedure – is to provide an answer to the conservation of these buildings, often having archaeological and artistic interest. In accordance with Life Cycle Assessment principles, the production process of the mortar can also be carried out at the restoration site, involving a low environmental impact. Thanks to its characteristics, the natural mortar object of this research study can represent a valid alternative to Portland cement.

Keywords

Circular economy, Natural mortar, Restoration site, Lime, Cocciopesto.

Santi Maria Cascone

DICAr - Dipartimento Ingegneria Civile e Architettura, Università degli Studi di Catania, Catania (Italy)

Matteo Vitale*

DICAr - Dipartimento Ingegneria Civile e Architettura, Università degli Studi di Catania, Catania (Italy)

Giuseppe Antonio Longhitano

Freelance, technologist natural mortar formulator

Giuseppe Russo

DICAr - Dipartimento Ingegneria Civile e Architettura, Università degli Studi di Catania, Catania (Italy)

Nicoletta Tomasello

Di3A - Dipartimento di Agricoltura, Alimentazione e Ambiente, Università degli Studi di Catania, Catania (Italy)

* Corresponding author:
e-mail: matteo.vitale@unict.it

1. INTRODUCTION

Several studies on historical monuments were carried out by the authors in order to analyse their building materials and their conservation status [1]. In most cases, investigations on mortars highlighted the presence of binders consisting of lime and *cocciopesto* – or pozzolanic materials. The understanding of how some buildings have been preserved in excellent condition for millennia, while others have deteriorated due to disintegration phenomena, has been an object of study by many research groups. The present research starts from the same ques-

tion and the desire – and the duty – to apply natural mortars in the restoration works.

One of the main research aims is to avoid the use of Portland cement or other building materials that may not be compatible with the existing ones and often involve pathologies (e.g., the *ettringite*). In accordance with the needs of a restoration site, the mortars to be used should, in fact, be durable and should ensure aesthetic performances. Moreover, new mixes from the reuse of recycled aggregates of the same restoration site



Fig. 1. The Nelson's Castle, which involves the reuse of recycled aggregates from the same restoration site.

should be used to respect the principles of the so-called *circular economy*. The circular economy, as opposed to the “linear” one, is defined as an “economy capable of self-creating” [2], because the waste (which should be disposed of in the usual evolution of the work) is “zero”, i.e. the waste material is totally reused increasing, although ideologically, the value of the work [3]. In order to be “circular”, a process should be based on the principle of sustainability [4] and on the use of materials having specific quality and maintenance requirements over time [5, 6].

According to the circular economy principles, the waste can be considered as a resource [7]. This resource can also be obtained from demolition materials of a restoration building site. In particular, the waste derived from the selective demolition, as can be deduced from the current legislation [8], is only reduced volumetrically and integrated with granules. Therefore, the chemical characterisation of the material is preserved [9]. This procedure meets the principle of the circular economy and defines a process of reuse that does not provide for physical-chemical transformations, and so can be performed at the same site.

By reusing building materials coming from the same restoration site, the decrease of environmental impact and the respect of the morphological nature of the building are both obtained [10].

2. THE MAIN COMPONENTS OF A NATURAL MORTAR

In restoration sites, the natural binder for the formulation of mortars is derived from the baking of calcium carbonate (CaCO_3). The products that can be obtained from the transformation of calcium carbonate are lime putty, milk of lime or powdered lime [11].

According to previous studies carried out on buildings of monumental interest, the used mortar is often composed of a lime-based binder [12]. A lime-based product hardens by carbonation after laying, becoming plaster through the evaporation of water. This compound presents calcium carbonate which, after baking and processing, becomes a soluble air binder. The original stone, after being transformed into a lime putty, totally modifies its characteristics. In fact, the obtained air binder becomes extremely soluble and is easily attachable in contact with water [13]. There is also natural hydraulic lime, obtainable from the baking of marlstone, having clay or silica nature. This hydraulic binder, called NHL, even without additions, allows formulating natural mortars with hydraulic character [14].

In order to be also used in a humid environment, the lime binder is often mixed with pozzolanic products having a hydraulic character which included, from the mineralogical point of view, sufficient silicon dioxide

[15]. The most used product is the *cocciopesto* having pozzolanic character, coming from grinding of *cotto* tile and obtained through the baking of blue clays. These elements, according to the principles of the circular economy, could derive from recycling processes on the restoration site [16, 17].

3. PORTLAND CEMENT

A material widely used in new constructions, after the use of traditional binders, is Portland cement [18, 19].

The high class of resistance of Portland cement and its very rigid elastic modulus prevent the use of this material on historical buildings. These characteristics prove the non-conformity of this material with the elasticity typical of masonry in general. Another problem concerning this material lies in its production method, which provides for the addition of the additives because of the blast furnace baking [20]. One of the main additives is gypsum, which is used as receptor retardant. After laying and drying, gypsum reacts with other soluble components (e.g. tricalcium aluminates) in the compound and degenerates into pathologies that cause the decay of cement. One of the degradation pathologies deriving from the use of the additives (and especially from the presence of gypsum) is the *ettringite*. This pathology is caused by the combination of residual lime with sulphates and gypsum [21, 22].

The formulation of Portland cement, although initially starts from the same mix of clay and lime, just for the baking pushed up and above 1500 °C defines complex compounds that degenerate into different pathologies, mainly by changing their durability. Due to its incorrect composition, Portland cement has a short life cycle, and therefore, its use should be avoided in the historical buildings to be restored. Several studies give the explanation for which it is no longer possible to use Portland cement in historical buildings, reporting the need to have a new formulation in place of Portland cement, possibly also applicable in new buildings [23, 24]. It is therefore stressed that the control of the mix should ensure, through its formulation, the absence of soluble residual elements after laying, in order to avoid pathologies.

The natural hydraulic binder, obtained through the application of this patented procedure, can be a valid alternative to Portland cement defined by a sustainable process with low environmental impact.

4. FORMULATION OF NATURAL MORTARS WITH HYDRAULIC BEHAVIOUR ACCORDING TO THE PATENTED PROCEDURE

Until today, it was impossible to establish the optimal quantities of clay/lime compounds, especially in relation to the mineralogical nature of the compounds, variable in the case of clay.

In the following paragraphs, the procedure for obtaining such a natural hydraulic binder is reported.

4.1. THE EQUATION OF VICAT

The equation of Vicat defines the relationship between lime and clay, which represents the hydraulicity index obtainable. The ratio of the mineralogical percentages of the single compounds is variable from 0.1 to 0.5, where the value of 0.5 defines the maximum hydraulicity of the compound (*eminently hydraulic lime*). The definition of this value, even if it falls within a defined range, is not enough to assure the absolute absence of residual free lime in the formulations used, nor therefore soluble parts in general.

4.2. AVOGADRO'S PRINCIPLE AND THE NEW INTERPRETATION OF THE VICAT EQUATION

The proposed procedure provides that in the Vicat formula, instead of an uncertain value belonging to a range of values, an optimum clay/lime ratio result of 1 is imposed. This assumption respects the principle of Avogadro, for which in the same volume, apart from the mass, the same number of atoms exists, combinable between elements of different nature. In this study, these elements are represented by calcium oxide and silicon dioxide, that combine to transform into calcium silicates, the only compound that guarantees natural hydraulicity to mortars.

This study, while focusing on the raw materials used, adopts a "new" Vicat equation that, although still valid

in the clay-lime ratio, defines a variable in the imposed result that must be exactly: clay/lime-ratio = 1.

The respect of the Vicat equation can be obtained by knowing the mineralogical nature of the used materials, always expressed in percentage ratio. According to this principle, a new mortar formulation could be optimised by varying the percentages of the compounds.

4.3. DENSITY

4.3.1. SEARCH FOR THE UNIQUE DENSITY FOR EACH NATURAL HYDRAULIC BINDER

As reported above, to obtain the perfect clay/lime combination, their mass ratio must be equal to one. Density is the principal parameter to be considered for the variation of the ratio. As widely known, the density is determined as the relationship between mass and volume. In particular, the compound density is given by the average value of the densities obtainable from each element of the raw material. So, each single density value has to be calculated.

The current technique to calculate the density in the laboratory is highly inaccurate because of measurement errors and the influence of relative humidity rate of each material. The solution for obtaining a specific value lies in the possibility of using the correlations between density, mass and volume.

4.3.2. DENSITY OF THE LIME

The density of the lime can be assumed as a single value. In fact, considering a lime CL 90 deriving from a pure rock with a concentration of Ca up to 98 %, the density is detectable from the periodic table and can be assumed as the first fixed value to be inserted in the denominator of the “new” formula of Vicat. In addition, its apparent density can be identified as unique.

4.3.3. AVERAGE DENSITY OF COCCIOPESTO

The above-optimised procedure for lime cannot be applied for clay, which is always composed by several variable elements having different mineralogical character-

istics (and, in the case of ground terracotta, also having different grain assortment).

The qualitative variation, obtainable for each new natural hydraulic binder, is therefore given by the characterisation of the used clay, which is composed of different elements expressed in percentages. The fundamental ones are the silica, the alumina and the iron, always contained but measurable in different percentages. These define specific densities for each clay, such to guarantee, through their average sums, a unique density and a unique apparent density.

The use of density as the main reference parameter for the evaluation of the apparent density, before in the lime and then in the clay, allows obtaining the values necessary to define the final data for the mixing of the new product.

The natural hydraulic binder is obtained from the percentages given by the calculated density ratio. So:

$$\%lime-density/\%clay-density = average\ density\ of\ the\ new\ hydraulic\ compound$$

Being the mass equal to density over volume, and defining the volume equal to 1 m³, the mass can be defined as density over 1. Then, the new hydraulic binder can be obtained as follows:

$$\%apparent\ density-lime/\%apparent\ density-clay = apparent\ density\ of\ the\ new\ hydraulic\ compound$$

It is perfectly balanced according to the principle of Avogadro. The absence of residual free lime is guaranteed by the complete combination of the calcium oxide and the elements in the *cocciopesto*.

In Matrix 1 (Fig. 2), are reported firstly the density values of Ca and the components of the *cocciopesto*, whose values can be taken from their datasheets. The ratio between the density given by Ca in the hydrated lime and the average density of the main elements of the *cocciopesto* Ca+Si+Al+Fe (there is indeed a 5-6% lime intake and other minor products negligible) provides the percentage to be used to formulate the new natural hydraulic binder, obtained by baking with a temperature that never exceeds 1000 °C.

The obtained lime and the ground terracotta can be preliminary even cold mixed. This method allows producing, in a sustainable way, the new natural hydraulic binder. The binder thus obtained and used in the formulation of new mortars leads, by combining with water, to the formation of calcium silicates.

By considering a volume equal to 1 m³, and by com-

ionisation energy by baking with a temperature below 1000 °C.

In the case study that involves the densities reported in Matrix 1, the percentages obtained to formulate the new natural hydraulic binder are:

- hydrated lime powdered: 36.73%
- *cocciopesto*: 63.27%

NATURAL BINDER DEPENDING ON THE COCCIOPESTO TESTED			DATA TO BE ENTERED <i>cocciopesto</i>				
COCCIOPESTO	DENSITY		mineralogical characteristics		% C. PESTO	% DENSITY	DENSITY
metal Alcalino Ter. Ca	1,54		8,42	8,42	9,14	0,14	AVERAGE
non metal Si	2,33		61,81	61,81	67,11	1,56	C. PESTO
other metal Al.	2,7		16,38	16,38	17,79	0,48	2,65
trans. metal Fe	7,86		5,49	5,49	5,96	0,47	
			92,1	92,1		2,65	
clay coefficient	14,43			0,921			
loss of fire	0,85%						
other negligible elem.	7,05%						
PERCENTAGE VERIFICATION BETWEEN LIME AND COCCIOPEST AS A FUNCTION OF THE COCCIOPEST USED							
	DENSITY	Percentage needed to saturate the combination of Calcium and Cocciopesto					
CALCIUM Ca	1,54	fixed index	% variable	36,73%			
metal Alcalino Ter. Ca							
non metal Si				VOLUME RATIO			
other metal Al.	2,65	variable index	% variable	63,27%			
transition metal Fe				kg/mc			
NEW DESIGN NATURAL HYDRAULIC BINDER MVA							
				DATA TO BE USED	NEW BINDING MIX		
				KG			
	4,19	LIME USED	530	HYDRATED LIME	36,73%	194,65	998,23
	0,0419	C. PESTO USED	1270	COCCIOPESTO	63,27%	803,58	
							NEW MVA BINDER
							998,23 NATURAL
							Kg/mc. HYDRAULIC

Fig. 2. Matrix 1, to be used for the formulation of the new hydraulic binder. The values reported for the densities of the components are exemplified.

paring the apparent densities of the elements, it is possible to establish – once calculated the density and the apparent density of the clay – the apparent density of the new compound.

Based on the procedure mentioned above, the use of the Matrix 1, which is part of the patented procedure, allows – by starting from the densities of the single elements – to obtain a new hydraulic binder given by the use of hydrated lime (always with 98% of CaO) and *cocciopesto* perfectly balanced.

Although the density values of the elements are invariable, it is not possible to say the same of their percentage in the mix. Indeed, by varying the percentage of the elements, the density of the clay also varies.

The ratio between the density given by Ca present in the hydrated lime and the average density of the main elements of the *cocciopesto* Ca+Si+Al+Fe provides the percentage to be used to formulate the new natural hydraulic binder. The binder is obtained with primary

The new apparent density of the natural hydraulic binder thus obtained is 998.23 kg.

Since the calcium oxide in the used lime and the elements in the *cocciopesto* are completely combined, there is not residual free lime.

5. THE MIX COMPOSITION AFTER OBTAINING THE NEW NATURAL HYDRAULIC BINDER

The current patent defines a procedure for the formulation of natural mortars with the use of a new natural hydraulic binder obtained by baking with a temperature below 1000 °C and preventive cold mixing. The core of the process lies in the possibility to create a “universal mortar”, as it can be used independently from the context and it is free from the pathologies induced by the use of Portland cement.

The definition of “universal mortar” refers to the possibility to use the mortar both at altitude zero above sea

FORMULATION IN VOLUME AND PERCENTAGES										BASE FOR CHARACTERIZATION OF NATURAL RAW MATERIALS										
IDENTITY	E. x kg.	0		N.1	c. client	€0,00														
IDENTITY materials used																				
Petrographic description	AGGREGATE	INERT	INERT	COCCIO	COCCIO	CALCFE	CALCFE	CALCFE												
stratified	LAVIC	LAVIC	PESTO	PESTO	CRYSTALLINE	OLUTICO	CRYSTALLINE													
traceability	invoice	86415/0316			33215/0316	1556n/231115	1557n/231115	1556n/231115												
AGGREGATES FOR MORTARS	AZOLO	AZOLO	C.PESTO	C.PESTO	TOMI CHINA B.	Y. MORI	GRANULATE	agg.	S.SILIC.											
DIMENSION Ø/D	UNI EN	0-3	0-500	0-500	0-1,3	0-1	0-500	500-800												
CE conformity marking	SI	SI			SI	SI	SI	SI	SI											
grading curve	mm	0-3	0-0,5	0-0,5	0-1,3	0-1	0-0,5	0,5-0,8	0-3											
category	GF35					4	4	1												
Thickness - Finesse	Fine					FP	MP	CP	Fine											
reaction to fire	Class A1	Class A1	Class A1	Class A1	Class A1	Class A1	Class A1	Class A1	Class A1											
hardness		4,31			5,25	1,75	1,75	3,24	0											
water absorption% (WA24)	1015-18-2004	1,79			0,84	4,4	4,3	1,43	0											
SOLUBLE MASS A.P.P.	1015-10	16,50	18,00	13,50	1370	1,500	1670	1370	1160	1180										
CHARACTERIZATION (p)						CaCO3	CaCO3	CaCO3	aggregate											
SiO2		45,55%			SiO2 61,81%	100%	100%	100%	7500%											
Al2O3		14%			Al2O3 16,38%															
Fe2O3		5,14			Fe2O3 5,49%															
CaO		10			CaO 8,42%															
minor compounds					min./7,7%															
pH					pH 10,2															
specific surface area					DET 2,80 m2/kg															
chromatic characteristics					intense red															
type of aggregate	Ø/D	0-3	0-500	0-500	0-1,3	0-1	0-500	500-800												
grading curve																				
PARTICLE SIZE DISTRIBUTION	1015-1																			
Sieve diameter	3.15 mm	100																		
	2.0 mm	85,3																		
	1.6 mm	69,9																		
	1.0 mm	51,8																		
	500 µm	33,7																		
	250 µm	2,0																		
	125 µm	1,0																		
	63 µm	3																		
VERIFICATION OF FREE LIME	WVA/0%Phase																			

Fig. 3. Matrix 3, containing the data collection of raw materials used for the realisation of natural mortars.

MIX finiture 1	project	LLAVIC	LLAVIC	COCCIOPESTO	COCCIOPESTO	CARBONATO B.	CARBONATO G.	GRANULATE	X	S.SILICEA		BINDER
GRADING CURVE	MM.	0-3	0-500	0-500	0-1,3	0-1	0-0,5	0,5-0,8	0-X	0-3		
		A	B	C	D = X	E	F	G	CHARACTERIZING	H		L1
input data	VOLUMES	1	0	0	3	1	0,5	1	0	0,1	AGGREGATE	2,64
9,24	% volum	10,82	0,00	0,00	32,47	10,82	5,41	10,82	0,00	1,08	% volumes	28,57

Fig. 4. Matrix 4, containing the volumes of the compounds to be inserted for the designed natural mortar. The project data expressed in volume and the percentages of aggregates and natural binder used are inserted.

MIX finiture 1	MVA	LLAVIC	LLAVIC	COCCIOPESTO	COCCIOPESTO	CARBONATO B.	CARBONATO G.	GRANULATO	X	S.SILICEA		L1
		0-3	0-500	0-500	0-1,3	0-1	0-500	500-800				
MVA aggregate+binders	1331,36	228,05	0,00	0,00	406,31	201,24	103,23	157,22	0,00	15,96	mva%	220,35
MIX finiture 1	LLAVIC	LLAVIC	COCCIOPESTO	COCCIOPESTO	CARBONATO B.	CARBONATO G.	GRANULATO	X	S.SILICEA		mva aggregate	L1
mva aggregate / mva binders	KG.	292,65	0,00	0,00	520,12	258,25	132,48	201,75	0,00	20,47	1425,72	998,23
MIX finiture 1	hardness	LLAVIC	LLAVIC	COCCIOPESTO	COCCIOPESTO	CARBONATO B.	CARBONATO G.	GRANULATO	X	S.SILICEA		L1
MIX hardness	3,37	0,60	0,00	0,00	1,68	0,23	0,12	0,37	0,00	0,00		0,39
MIX finiture 1	WATER ABS. %	LLAVIC	LLAVIC	COCCIOPESTO	COCCIOPESTO	CARBONATO B.	CARBONATO G.	GRANULATO	X	S.SILICEA		L1
X water absorption % (WA24)	2,50	0,25	0,00	0,00	0,27	0,57	0,23	0,15	0,00	0,00		0,97
kg. Materials/E	input data	LLAVIC	LLAVIC	COCCIOPESTO	COCCIOPESTO	CARBONATO B.	CARBONATO G.	GRANULATO	X	S.SILICEA		L1
MQ TO BE WORKED	1											L1
INCIDENCE KG PER MQ	3	kg.		kg.		kg.		kg.		kg.	ald/b	kg.
KG TOT.	3	0,41	0,00	0,00	0,957	0,39	0,20	0,34	0,00	0,03	3	0,66

Fig. 5. Matrix 5, containing "immediate" check of the natural mortar obtained from Matrix 4.

level and over than 1000 m. Indeed, the mix does not need physical-chemical differentiations depending on the altitude above sea level. Moreover, additives to withstand frost or brackish water are not required by the mixture. Furthermore, each mixture, respecting the morphological characteristic of the building, involves a primary aggregate characterising the others.

Following, the steps necessary to obtain a formulation type – extracted from the patented calculation program – are reported.

In the Matrix 3 (Fig. 3) all the mineralogical characteristics and the technical data of the used raw materials are reported. In the Matrix 4 (Fig. 4) the data of the formulated mix, expressed in volumes and percentage, are reported. Matrix 5 (Fig. 5) shows the data generated by the project mix in order to obtain immediate feedback of the physical-chemical characteristics of the formulation. In particular, apparent density, water absorption and hardness are shown.

6. OBTAINING THE CHROMIA OF THE NATURAL MIX

The range of natural aggregates, unique for each project mix, allows obtaining different natural colours, possible without dye pigments. The tonality of the final plaster is given by the sum of the chromatic qualities, unique for each aggregate used.

In the mix used in the project, obtained with a cold procedure, colours of primary subtractive (cyan, yellow and magenta) were chosen. Their proper use (i.e. in the appropriate quantities of volume), allows having wide chromatic ranges. From a close distance, it is possible to see the colours of the aggregates used, and from an adequate distance, it is possible to see the predominant colour (Fig. 6). The reuse of aggregates from the same building site allows respecting the morphology of the places.

Below is reported an example of mortar obtained through the illustrated procedure and applied to the Church of Purity of Catania (Fig. 7).

		PROCESSING IN PERCENTAGE 100 % BASE WORKED															
MIX IV																	
INPUT DATA				COCCOPESTO	C.PEST	S.SILICEA	YELLOW MURI	T.WHITE	GRANULOSA	LLAVICO	LLAVICO			NHL	WHITE	VOLUMES	
				0-500	0-1,3	0-3	0-500	0-1	500-800	0,5	0,3	L1	0-1	0-2	0,00	0,0880	FUNCTION%
SAMPLE	PERCENTAGE		VOLUMES	0,00	3,00	0,10	0,50	1,00	1,00	0,00	1,00	0,00	0,00	0,00	0,00	100	
DETECTED	255-240%	%		0,00%	45,455	1,515	7,575	15,152	15,152	0,000	15,152	0,000	0,000	0,00%			255-240%
173	0,68	0,439	red		95,45	3,11	16,89	38,18	37,12	0,00	20,30	0,00	correct	0,54%	173,939	0,682	
128	0,50	0,325	green		50,91	2,65	16,36	38,48	37,88	0,00	21,36	0,00		1,38%	129,773	0,509	
93	0,36	0,236	blue		14,09	2,23	14,92	38,64	38,18	0,00	23,64	0,00		0,55%	93,515	0,367	
72	0,30		TONALITY		8,18	0,29	2,20	20,15	19,85	0,00	22,27	0,00			72,939	0,304	
147	0,61		SATURATION		80,91	1,33	5,23	36,36	19,55	0,00	3,64	0,00			147,015	0,613	
146	0,61		BRIGHTNESS		51,36	2,52	0,00	36,21	35,45	0,00	20,61	0,00			146,152	0,609	

Fig. 6. Matrix 2, to be used to identify the volumes in the project and to detect the final colour.



Fig. 7. Church of Purity of Catania: close view of the mortar (on the left) and perspective view (on the right).

In this case study, in Matrix 4 (Fig. 4), the following project data were applied:

-D=X=42.86% – base colour characterising aggregate

-A=14.24% – inert basalt lava structural aggregate

-G=14.24% – white crystalline carbonate structural aggregate

-F=7.14% – yellow carbonate aggregate used for basic chromatic variation X=D

-H=1.42% – aggregate used for surface's chromatic characterisation

Aggregate=79.90%

New binder L1=20.10%

7. THE PRODUCTION CHAIN OF NATURAL MORTARS ON SITE

In compliance with the principles of the circular economy, the waste coming from the building to restore becomes a resource [25]. This research study aims to formulate natural mortars on-site, by respecting and maintaining the initial characterisation of the materials, even after the intervention.

Besides not being compatible with the final product, premixed products require a chain of production and processing characterised by high environmental impact, because it involves physical-chemical transformations and multiple kinds of transport. The production process presented in this paper does not follow this chain.

Once the mineralogical nature of the individual raw materials has been verified, mortar can be formulated by mixing the cold sands, so without the use of ovens for preventive drying. The mortar is obtained by mixing the aggregates and the new binder in a cement mixer with water in established volumetric doses. The inert aggregates used for the composition of such mortars shall be as pure as possible to minimise the “uncontrolled” soluble parts, which could be the future cause of deterioration pathologies for plaster, both chemical and mechanical. The aggregates, in fact, can be inert or hydraulically active, and in the second case, they can contain substances that react post-work. Therefore, it is essential also to verify that they are inert and using



Fig. 8. Restoration site where the mortar was used – “Palazzo Porto” Catania.



Fig. 9. Restoration site where the mortar was used – “Palazzotto Bis-cari”; Catania.



Fig. 10. Restoration site where the mortar was used - “Real Collegio Capizzi”, Bronte (CT).

them properly as mortar structure with different particle size curves.

The volume ratio between aggregates and binders is controllable and affects only the elastic module. This allows a possible variation of stiffness that can be modulated for specific purposes and requirements, conforming to historical walls.

In the following, some examples in which the presented mortar was applied are reported (Figs. 8–12).

8. CONCLUSION

The current study is based on the process for the formulation of natural mortars with the use of a new natural hydraulic binder. The study is the result of applied research, carried out also through construction laboratories that sometime lasted more than 15 years. This has allowed the authors a long observation of the behaviour of the formulated natural mortars and progressive improvement of the procedures. The final product is free from corrective additives and industrial substances.

The process, developed for the formulation of natural mortars also in situ, is covered by a twenty-year patent that is increasingly used in restoration sites. The patent, which started from the inherited knowledge, has led to defining an innovative and sustainable solution.

The sustainability principles are respected thanks to recycling of aggregates from inert and to formulating the mixes on site. This allows to eliminate in the production process of mortars the use of industrial products, which are strongly impacting on the environment and do not respect the intrinsic identity of a historical building, that must be preserved. Due to its durability and the low maintenance required, the new natural hydraulic binder can be considered as an alternative to Portland cement, even in modern buildings.

9. REFERENCES

- [1] Cascone S, Longhitano G, Russo G, Tomasello N (2018) Sustainable Recycling in Architectural Restoration: the Use of Natural Mortars. In: BRAU4 Proceedings
- [2] Coste-Maniere I, Croizet K, Sette E, et al (2019) Circular economy: A necessary (r)evolution. In: Muthu SS (ed) Circular Economy in Textiles and Apparel. Woodhead publishing, pp 123–148
- [3] Nakamura S, Kondo Y, Nakajima K, et al (2017) Quantifying Recycling and Losses of Cr and Ni in Steel Throughout Multiple Life Cycles Using MaTrace-Alloy. *Environ Sci Technol*. <https://doi.org/10.1021/acs.est.7b01683>
- [4] Goodland R (2017) The concept of environmental sustainability. In: Sustainability
- [5] Gardetti MA (2019) Introduction and the concept of circular economy. In: Muthu SS (ed) Circular Economy in Textiles and Apparel. Woodhead publishing, pp 1–10
- [6] Iacovidou E, Velis CA, Purnell P, et al (2017) Metrics for optimising the multi-dimensional value of resources recovered from waste in a circular economy: A critical review. *J Clean Prod* 166:910–938
- [7] Zhijun F, Nailing Y (2007) Putting a circular economy into practice in China. *Sustain Sci* 2:95–101
- [8] D.lgs. 13 Gennaio 2003 n. 36. art. 2
- [9] D.lgs. 3 Agosto 2005. art. 5
- [10] Lockrey S, Verghese K, Crossin E, Nguyen H (2018) Concrete recycling life cycle flows and performance from construction and demolition waste in Hanoi. *J Clean Prod*. <https://doi.org/10.1016/j.jclepro.2017.12.271>
- [11] Elert K, Rodriguez-Navarro C, Pardo ES, et al (2002) Lime mortars for the conservation of historic buildings. *Stud Conserv*. <https://doi.org/10.1179/sic.2002.47.1.62>
- [12] Arizzi A, Viles H, Cultrone G (2012) Experimental testing of the durability of lime-based mortars used for rendering historic buildings. *Constr Build Mater*. <https://doi.org/10.1016/j.conbuildmat.2011.10.059>
- [13] Van Balen K, Van Gemert D (1994) Modelling lime mortar carbonation. *Mater Struct*. <https://doi.org/10.1007/BF02473442>
- [14] Lanas J, Bernal JLP, Bello MA, Galindo JIA (2004) Mechanical properties of natural hydraulic lime-based mortars. *Cem Concr Res*. <https://doi.org/10.1016/j.cemconres.2004.02.005>
- [15] Ghrici M, Kenai S, Said-Mansour M (2007) Mechanical properties and durability of mortar and concrete containing natural pozzolana and limestone blended cements. *Cem Concr Compos*. <https://doi.org/10.1016/j.cemconcomp.2007.04.009>
- [16] Kisku N, Joshi H, Ansari M, et al (2017) A critical review and assessment for usage of recycled aggregate as sustainable construction material. *Constr Build Mater* 131
- [17] Limbachiya M, Meddah MS, Ouchagour Y (2012) Use of recycled concrete aggregate in fly-ash concrete. *Constr Build Mater*. <https://doi.org/10.1016/j.conbuildmat.2011.07.023>
- [18] 5th Historic Mortars Conference (2019)
- [19] Varas MJ, De Buergo MA, Fort R (2005) Natural cement as the precursor of Portland cement: Methodology for its identification. *Cem Concr Res*. <https://doi.org/10.1016/j.cemconres.2004.10.045>
- [20] Aitein PC (2016) Portland cement. In: Science and Technology of Concrete Admixtures. Cambridge
- [21] Bakharev T, Sanjayan JG, Cheng YB (2002) Sulfate attack on alkali-activated slag concrete. *Cem Concr Res*. [https://doi.org/10.1016/S0008-8846\(01\)00659-7](https://doi.org/10.1016/S0008-8846(01)00659-7)
- [22] Glasser FP, Marchand J, Samson E (2008) Durability of concrete - Degradation phenomena involving detrimental chemical

- reactions. *Cem Concr Res*. <https://doi.org/10.1016/j.cemconres.2007.09.015>
- [23] Silva BA, Ferreira Pinto AP, Gomes A (2015) Natural hydraulic lime versus cement for blended lime mortars for restoration works. *Constr Build Mater*. <https://doi.org/10.1016/j.conbuildmat.2015.06.058>
- [24] Juenger MCG, Winnefeld F, Provis JL, Ideker JH (2011) Advances in alternative cementitious binders. *Cem Concr Res* 41(12): 1232–1243
- [25] Silva RV, de Brito J, Dhir RK (2017) Availability and processing of recycled aggregates within the construction and demolition supply chain: A review. *J Clean Prod* 143:598–614